

# Self-Seal® GG-266 INTUMESCENT SILICONE FIRESTOP SEALANT



Before ordering, consult Self-Seal® firestop listings to confirm that there is a firestop system for your particular site condition. Self-Seal® MECHANICAL and ELECTRICAL APPLICATION CHARTS can be used as a quick reference. Self-Seal® GG-266 is only recommended for use in firestop systems that are listed in the APPLICATION GUIDELINES FOR Self-Seal® GG-266 SILICONE INTUMESCENT FIRESTOP CAULK.

Self-Seal® GG-266 is a single-component, neutral cure, non-slumping intumescent silicone caulk that is designed to seal combustible service penetrations in fire-rated walls and floors. When exposed to temperatures in excess of 150°C (300°F) it will begin to expand. As the combustible penetrating item softens and collapses under fire conditions, the silicone composition will rapidly intumesce to fill the void with a patented char composite that contains expanded graphite.

## ■ FEATURES & TYPICAL USES:

### Features:

- Intumescent Silicone (expands when exposed to temperatures in excess of 150°C (300°F))
- Non-sag silicone
- Water resistant before, during, and after cure
- Freeze-thaw stable
- Protects your wall & floor openings
- Tested at positive pressure to simulate the pressure differentials that can occur in a fire situation

Self-Seal® GG-266 seals combustible service penetrations in fire and smoke rated wall or floor separations.

Basic uses include firestopping:

- Up to 2" PVC, ABS, IPEX Aquarise, PEX, FRPP, and CPVC penetrations - only a minimum 5/16" annular space needed
- Up to 4" PVC, IPEX XFR 15-50 PVC, Royal Pipe HRS2550, ABS, and CPVC pipe penetrations through conical or cored openings in concrete floor slabs

## ■ LIMITATIONS:

**NOT SUITABLE FOR ELECTRICAL PENETRATIONS.**

## ■ SURFACE PREPARATION & APPLICATION:

**Before Use:** Read the label in its entirety.

### Surface Preparation:

- Surfaces must be structurally sound, clean, dry, and free from oil, grease, water, dirt, or any other material and membranes that may deter adhesion.

### Application:

1. See application guidelines for information regarding installation.
2. Follow all instructions in system/listing for each application. If you need help, call us at 1-800-853-3984.

### Clean-up:

1. Uncured Self-Seal® GG-266 silicone firestop cannot be removed with water.
2. Remove the bulk of the uncured sealant with a plastic scraper, being careful not to compress it into cracks or crevices.
3. Use a cloth saturated with mineral spirits, acetone, or denatured alcohol to wipe away any remaining silicone.
4. Clean surface with soap and water if possible.

### Chemical Resistance & Durability:

1. At ambient temperatures, the fully set silicone sealant can temporarily withstand:
  - a. 15% diluted acids and bases
  - b. Majority of common cleaning agents and disinfectants (excluding those containing iodine)
2. Silicone rubber will degrade gradually if exposed to strong acids and bases.



**SELF-SEAL®**  
FIRESTOPPING PRODUCTS

# Self-Seal® GG-266 INTUMESCENT SILICONE FIRESTOP SEALANT

## TYPICAL PROPERTIES:


These values are not intended for use in preparing specifications. Spec Writers; please contact NUCO Inc. before writing specifications if any further information is required.

Description	Specification
<b>As Supplied...</b>	
Type:	One part silicone sealant
Cure method:	Neutral, moisture cure
Specific gravity:	1.25
Working time:	20 - 40 minutes
Application temperature range:	-29° to 50°C (-20° to 122°F)
Full cure / adhesion:	14 - 21 days

### As Cured - Physical - after 7 days at 25°C (77°F) and 50% relative humidity...

Free Expansion Volume:	>6 times original volume: Heated to 350°C (662°F)	
ASTM C1299 - service temperature range:	-40° to 110°C (-40° to 230°F)	
ASTM E-84 - surface burning characteristics:	FSI = 0	SD = 27
ASTM G21 - fungal resistance rating:	No growth = 0	

\*These values are for general information and not for specification purposes.



Subject to the Conditions of Approval as a Wall & Floor Penetration Firestop when installed as described in the current edition of the Factory Mutual Research Approval Guide.



## SPECIFICATIONS:

**Self-Seal® GG-266 Intumescent Silicone Firestop Sealant** meets:

- ASTM E-814
- ANSI / UL1479
- UBC 7-5
- CAN/ULC-S115
- South Coast AQMD Rule 1168 Compliant
- Self-Seal® GG-266 has achieved GREENGUARD GOLD Certification

FBC™ System Compatible indicates that this product has been tested, and is monitored on an ongoing basis, to assure its chemical compatibility with FlowGuard Gold®, BlazeMaster® and Corzan® piping systems and products made with TempRite® Technology. The FBC System Compatible Logo, FBC™, FlowGuard Gold®, BlazeMaster®, Corzan®, and TempRite® are trademarks of Lubrizol Advanced Materials, Inc. or its affiliates.

**Disclosure:** The information and data contained herein is BASED ON INFORMATION WE BELIEVE TO BE RELIABLE. Please read all statements, recommendations or suggestions herein in conjunction with our CONDITIONS OF SALE which apply to all goods supplied by us. We assume no responsibility for the use of these statements, recommendations or suggestions, nor do we intend them as recommendation for any use which would infringe any patent or copyright.

## STORAGE AND SHELF LIFE:

- Shelf life is 24 months from the date of manufacture when stored in a clean, dry area.
- Store between 10° to 25°C (50° to 77°F).
- For best results, store the sealant in tightly closed containers when not in use.

## CAUTION:

- Use in well ventilated areas and avoid breathing vapours.
- On contact, uncured sealant irritates eyes. Flush eyes with lukewarm water. Call physician.
- Avoid skin contact and DO NOT ingest.
- Consult Safety Data Sheet.

## PRIMING:

Normally Self-Seal® GG-266 does not require priming for most common building materials. A trial application is recommended before commencement of a project.

## 50 YEAR DURABILITY STATEMENT:

Material will remain elastic in nature for 50 years. Independent tests indicate that silicone sealant will withstand outdoor weathering for 50 years without significant performance changes. This statement applies to the sealant itself and not to the substrates to which it is bonded to. In the event of elasticity failure, return original container and sales receipt to Nuco Inc. NUCO's liability, expressed or implied is limited to the stated selling price of any goods found to be defective.

## MANUFACTURER INFORMATION:

NUCO Inc. 150 Curtis Drive  
Guelph, ON N1K 1N5

T: 519-823-4994  
F: 519-823-1099

TF: 1-800-853-3984  
E: info@nucoinc.com

## AVAILABLE SIZES & COLOURS:

SKU	Colour	Size	Format
26639	Red	300 mL	Cartridge
26659	Red	591 mL	Sausage
26619	Red	10 L	Pail

## LIMITED WARRANTY INFO:

NUCO Inc., warrants only that its product will meet its specifications for a period of 12 months following date of manufacture. NUCO shall in no event be liable for incidental or consequential damage, or improper storage. NUCO's liability, expressed or implied is limited to the stated selling price of any goods found to be defective.